



Cotton Association Of India

COTTON TESTING & RESERACH LABORATORY

210, Toral Complex, 2nd Floor, Jawahar Road, Rajkot-360 001, Tel.No.3047537/38, Fax-2225256

H.O. : Cotton Exchange Bldg., 2nd Floor, Opp. Cotton Green Railway St., Cotton Green.

Mumbai- 400 033. Tel : +022-65186830

Fiber Test Report No 1752

Date : 26/11/2011

Samples of cotton submitted by :

Rajkot

SAMPLE DETAILS FURNISHED BY THE PARTY						HVI- (HVI Mode Test Results)									
Lab	Station	Variety	Lot No.	Press Running	SB	UHML	ML	UI	Tenacity at	ELG	MIC	COLOUR			SFI
Ref No.				No.	No.	(mm)			3.2mm (g.tex)	%		Rd	+b	CG	
11/11629	Rajkot	V-797	A Grade	5401	-	21.6	16.9	78.2	19.8	6.4	4.2	69.4	9.2	42-2	16.1
11/11630	Rajkot	V-797	A Grade	3201	-	23.4	18.5	78.9	21.8	6.1	4.4	71.7	11.3	33-1	14.5
11/11631	Rajkot	V-797	B Grade	8101-8200	-	21.1	16.4	77.8	16.0	6.5	3.9	69.7	10.0	42-1	16.8
11/11632	Rajkot	V-797	B Grade	8001-8100	-	20.8	16.3	78.1	16.0	6.3	4.3	67.8	10.1	43-2	16.8

SAMPLE DETAILS FURNISHED BY THE PARTY-Sample Tested on Trash Seperator

Lab	Station	Variety	Lot No.	Press Running	S.B.	Lint %	Trash %	Cage
Ref No.				No.	NO.			Loss %
11/11629	Rajkot	V-797	A Grade	5401	-	79.2	19.56	1.3
11/11630	Rajkot	V-797	A Grade	3201	-	78.6	20.28	1.1
11/11631	Rajkot	V-797	B Grade	8101-8200	-	76.0	22.98	1.0
11/11632	Rajkot	V-797	B Grade	8001-8100	-	75.1	23.68	1.2

Tested :- RH 65± 2 % and Temp 27 ± 2° c

NOTES:-

- 1 Samples are not drawn by the Laboratory
- 2 The test results relate only to the item tested.
- 3 This report shall not be used for litigation or publicity.
- 4 This report shall not be reproduced in part/ full without the written permission of the Laboratory.

Lab Tech.